

Magnetization Jump in a Model for Flux Lattice Melting at Low Magnetic Fields

Seungoh Ryu and D. Stroud

Department of Physics, Ohio State University, Columbus, Ohio 43210

(Received 31 March 1997)

Using a frustrated XY model on a lattice with open-boundary conditions, we numerically study the magnetization change near a flux lattice melting transition at low fields. In both two and three dimensions, we find that the melting transition is followed at a higher temperature by the onset of large dissipation associated with the zero-field XY transition. It is characterized by the proliferation of vortex-antivortex pairs (in 2D) or vortex loops (in 3D). At the upper transition, there is a sharp increase in magnetization, in qualitative agreement with recent local Hall probe experiments. [S0031-9007(97)03418-2]

PACS numbers: 74.60.Ge, 64.60.Cn

Among the most debated aspects of high- T_c superconductors is the nature of the superconducting transition in a magnetic field. It is widely believed that, in the presence of disorder, the transition may fall into the universality class of a vortex glass [1] or a Bose glass [2]. In addition, disorder may produce an entirely new transition characterized by the disappearance of the Bragg peaks of the Abrikosov lattice above a certain magnetic field [3]. But even in the absence of disorder, the phase transition is not fully understood. At high applied fields \mathbf{H} parallel to c , several numerical studies strongly suggest that there is a *first-order* phase transition with a finite latent heat [4–6] and a corresponding magnetization discontinuity [5]. At lower magnetic fields, the evidence is more ambiguous. At such fields, the thermodynamics of the field-induced vortices should be strongly influenced by fluctuations of the zero-field XY degrees of freedom, which are far more numerous than the *field-induced* vortex degrees of freedom [7].

Experimental evidence for a first-order transition with a magnetization jump has been reported for both $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ [8] and $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ [9]. These measurements show that the transition is accompanied by an *increase* in vortex number density, suggesting a melting analogous to that of water.

In this paper, we present model calculations of the superconducting-normal (S - N) transition in both two and three dimensions (2D and 3D) in the absence of disorder. Our results strongly suggest that, in both cases, the S - N transition at low B occurs in *two distinct stages*. The first is the melting of the vortex lattice at T_m , and is characterized by the disappearance of the Bragg peaks associated with solid order. The second stage is driven by the XY degrees of freedom, and occurs at temperatures above T_m . That zero-field XY transition is accompanied by the unbinding of vortex-antivortex pairs (in 2D) or proliferation of vortex loops (in 3D) [10]. In either case, these excitations screen the repulsive interactions between the field-induced vortices or vortex lines [11]. Consequently, the density of field-induced vortices becomes larger, leading to an increase in the absolute magnetization as observed

experimentally. In 3D, this screening is accompanied by the vanishing of γ_{zz} , the z component of the helicity modulus, which measures the rigidity of the phase degrees of freedom in the c direction [12]. Since this occurs at a sharp temperature, the second stage could be a true phase transition in 3D.

Our calculations are based on the widely studied frustrated XY model on a stacked triangular lattice [4]. This model has the Hamiltonian $\mathcal{H} = -\sum_{\langle ij \rangle} J \times \cos(\theta_i - \theta_j - A_{ij})$, where θ_i is the phase of the superconducting order parameter at site i , J is the isotropic coupling energy between nearest-neighbor sites, and $A_{ij} = (2\pi/\phi_0) \int_i^j \mathbf{A} \cdot d\mathbf{l}$ accounts for any applied magnetic field \mathbf{B} through a vector potential \mathbf{A} . The choice of a triangular grid minimizes the periodic vortex pinning potential which is an artifact of any discrete lattice [13]. We evaluate the equilibrium and dynamical properties of \mathcal{H} using, respectively, a standard Monte Carlo (MC) procedure [14], and solving the coupled Josephson equations with Langevin dynamics [15]. For each plaquette p , we determine a vorticity vector $n_\alpha(p)$ ($\alpha = x, y, z$) from $\sum_p \text{mod}[\theta_i - \theta_j - A_{ij}, 2\pi] = 2\pi[n_\alpha(p) - f_p]$. Here the summation runs along the bonds $\{i, j\}$ belonging to the plaquette labeled p , and $f_p \equiv \sum_p A_{ij}/(2\pi)$.

Previous calculations [4] have established that there is a *first-order* phase transition at high fields in the c direction ($f \equiv \phi/\phi_0 = 1/6$, where ϕ is the flux per triangular plaquette and $\phi_0 = hc/2e$). At low fields ($f = 1/25$) on a simple cubic lattice [14], there is an apparent double transition: The first stage is a melting transition, followed at higher temperatures by a loss of phase coherence parallel to the c axis (as measured by γ_{zz}). By contrast, Jagla *et al.* found that, for $f = 1/6$, the transitions are separate only in the presence of quenched disorder [16].

We first show that a similar double transition occurs in the stacked triangular lattice. Figure 1 shows $\gamma_{zz}(T)$, the c -axis resistance $R_c(T)$, and the first-order Bragg peak intensity $I(\mathbf{G}_1, T)$ (inset) as a function of temperature T for $f = 1/24$. \mathbf{G}_1 is taken as one of the six equivalent shortest reciprocal lattice vectors in the a - b plane.




FIG. 1. Helicity modulus γ_{zz} (filled circles) and c axis resistance R_c (open circles) in units of $1/t_0$, where $t_0 = \hbar/(2eJR)$. The error bars for R_c show the standard deviation when the averaging interval was varied from $200t_0$ to $600t_0$ in steps of $10t_0$. The inset shows the integrated first-order Bragg intensity $I(\mathbf{G}_1)$ of the field-induced vortices, for $f = 1/24$. Error bars represent rms deviation over seven different configurations 7000 MC steps apart. Lines are guides for the eyes.

We use periodic boundary conditions in all three directions and a lattice which is a parallelepiped of size $24 \times 24 \times 24$, i.e., 48 vortex lines. Clearly, $I(\mathbf{G}_1)$ and γ_{zz} go to zero at *quite different* temperatures, suggesting a double transition. The lower temperature, denoted $T_m \sim 1.55J$, corresponds to the loss of solidlike structural order. The upper transition occurs at $T_\ell \sim 2.0J$. The behavior $T_m < T < T_\ell$ is characterized by logarithmically slow relaxation of γ_{zz} to its nonzero equilibrium values over $(5-10) \times 10^5$ MC sweeps. The small high- T tail of γ_{zz} depends on sample thickness, and the data shown in the figure represent asymptotic behavior up to $N_z = 48$. Starting from typical equilibrium configurations thus obtained, we carried out dynamical calculations within the resistively shunted Josephson junction model [15,16]. Using periodic boundary conditions, we injected a uniform current ($0.083I_c$ per grain) through the lowermost x - y plane and extracted through the x - y plane in the middle of the sample, effectively creating a periodic pattern of alternating current flow along the z axis. The resulting dissipation R_c is sensitive mainly to the presence of *net transverse vorticity* and its fluctuations. We also calculated R_{ab} , analogous to the in-plane resistivity, again using a similar periodic arrangement. This exerts a *shearing* force on two halves of the lattice and probes directly the shear rigidity of the lattice on length scales of our simulation box. The qualitative behavior of R_{ab} is very similar to R_c , i.e., it displays a sharp increase at T_ℓ [17].

Figure 2 shows the top-to-bottom vorticity density-density correlation function $g_{tb}(x, y) \sim \langle n_z(x, y, z = N_z/2)n_z(0, 0, 0) \rangle$ as a function of T for $f = 1/24$. Note the periodic lattice of peaks at $T/J = 1.5$, the presence of only a strong central peak at $T/J = 1.8$, and the absence of peaks at $T/J = 2.2$. The strong central peak suggests




FIG. 2. *Top-to-bottom* vortex density-density correlation function $g_{tb}(x, y)$ for $T/J = 1.5, 1.8,$ and 2.2 in a $24 \times 24 \times 24$ system with $f = 1/24$. $T_m \sim 1.55J$ and $T_\ell \sim 2.0J$. The lower panel shows typical vortex configurations.

that at $T/J = 1.8$ the vortex lattice has melted into a *line liquid* with a *finite* line correlation length along the field direction. This separation between the melting and γ_{zz} transition is a *low-field* phenomenon: At $f = 1/6$, the $I(\mathbf{G}_1)$ and γ_{zz} vanish at *nearly the same* T within our resolution.

To probe the vortex density change associated with the transitions, we must abandon periodic boundary conditions because these enforce a fixed density in the system, whose value is dictated by the applied field. We therefore adopt *free transverse* boundary conditions [18], while still maintaining periodic boundary conditions in the z direction. This procedure allows the outermost surface of the vortex ensemble to have a variable position.

We first discuss our results in 2D, considering $f = 1/24$ on a triangular grid of different sizes with $N = 26, 52, 78,$ and 100 . One might think of taking the “magnetization” M_z as the average net vortex density $n \equiv \int n_z(\mathbf{r})d\mathbf{r}/A$, where $n_z(\mathbf{r})$ is the local vortex density and A is the total area. However, M_z defined in this way suffers from spurious boundary effects, arising from the depletion of vortices near the boundaries in the lattice phase. This surface effect [19] vanishes for large samples as $1/\sqrt{A}$. Instead, we look at the *local Voronoi cell area* \mathcal{A}_i , i.e., the area of the generalized Wigner-Seitz cell for vortex i [6]. A local vortex density at a point \mathbf{R} in the simulation box may then be defined as $n(\mathbf{R}) = \sum_i \delta(\mathbf{R} \in \mathcal{A}_i)/\mathcal{A}_i$, where $\delta(\mathbf{R} \in \mathcal{A}_i)$ gives 1 if the point \mathbf{R} lies in the Voronoi cell associated with vortex i . Next, the local magnetization M_z which we equate with the *bulk average density* $\langle n \rangle$ is calculated from $\langle n \rangle = \sum_{\mathbf{r} \in C} \frac{1}{\mathcal{A}_i}$ as the average of the inverse Voronoi area for vortices lying within a measurement area C suitably distant from the sample boundary.

For $T \geq 0.5J$, there are, besides the field-induced vortices, numerous thermally induced vortex-antivortex dipole pairs, which must be eliminated before this procedure is applied. To do this, we pair each antivortex

with the nearest vortex, and remove them from the count. Since most such dipole pairs are much smaller than $1/\sqrt{\langle n \rangle}$, this criterion is justified.

For $f = 1/24$ the 2D melting transition occurs near $T_m^{2D} = 0.09J$, as determined by the vanishing of the Bragg peak $I(\mathbf{G}_1)$. The zero-field XY (i.e., in 2D, the Kosterlitz-Thouless) transition occurs at about $T_{KT}^0 = 1.6J$. Superconductivity in 2D is destroyed at T_m^{2D} . As shown in Fig. 3, $\langle n \rangle/n_0$ (where $n_0 \equiv \sqrt{3}f/4$ is the nominal density) displays a sizable increase across T_{KT}^0 . This increase is independent of system size (checked up to 100×100 grains). As further evidence that the boundaries are not producing this increase, we note that we obtain the same results for $\langle n \rangle$ for different choices of measurement areas, C_1 and C_2 .

The upper panel of Fig. 3 shows that the local density fluctuates progressively more as T increases: Near T_m , the rms width of the local bond length fluctuation is about 0.15, a value close to the Lindemann number. The increase in density at high temperatures arises mainly from an increase in the frequency of short bonds, which occur *throughout the sample* as is clear from the panel. We have also observed at T_m a sharp jump in the density of *topological lattice defects*, such as disclinations. If these defects are predominantly of a particular type such as lattice vacancies, we would expect a corresponding jump in vortex density. However, we do not observe a sizable increase in M_z at T_m within our resolution of about 2%.

As the vortex liquid is further heated, the vortex density *increases* to a value well above that of the solid. This increase is due to the excitation of vortex-antivortex pairs




FIG. 3. Upper panel: local density distribution $n(\mathbf{R})$, plotted as a function of distance R from the center of the plane for $T/J = 0.08, 1.05,$ and 2.05 . Lower panel: normalized bulk vortex density vs T for three different sample sizes at $f = 1/24$. Right panel: results of Delaunay triangulation for field-induced vortices at $T/J = 1.05$. For the results in the left panel, averages were taken over vortices within two different bounded areas, C_1 and C_2 .

characteristic of the $f = 0$ Kosterlitz-Thouless transition. The excited pairs screen the repulsion between the field-induced vortices, lowering the effective chemical potential for field-induced vortices and making the system more compressible.

Figure 4 shows the corresponding behavior in 3D, at $f = 1/24$ and $1/6$. Once again $n/n_0 \sim 1$ below the zero-field 3D XY transition at T_{XY} , increasing markedly near $T/J \sim 2.0$ for $f = 1/24$ and near $1.15J$ for $f = 1/6$. For $f = 1/6$, this increase occurs over a temperature range $\Delta T < 0.05J$, just at the first-order phase transition, where both lattice order and phase coherence parallel to the field are destroyed ($T_m \sim T_\ell$ for $f = 1/6$). The relative change in vortex density, $\delta n/n_0$, is less than 7% for $f = 1/6$. The entropy as calculated from $\int^T C/TdT$ displays a corresponding jump $\Delta S \sim 0.11k_B$ per grain (or $0.3k_B$ per vortex) as shown in the upper panel.

For $f = 1/24$, the change in n/n_0 is spread over a wider temperature range ($\Delta T \sim 0.7J$), and the midpoint of the increase in n/n_0 falls at T_ℓ . The overall field change $\delta B/B \sim 15\%$. The entropy does not show a recognizable jump near T_m . For this open-boundary system, $T_m < 1.35J$, about 10% below the value $T_m \sim 1.55J$ found with periodic boundary conditions. At $f = 1/6$, the two transitions are indistinguishably close, and any possible change associated with melting is overshadowed by the larger *increase* in n due to screening by vortex loops at T_ℓ for this dense system. Thus, for $f = 1/24$, there is a phase between T_m and T_ℓ with no lattice order, but yet with a diamagnetic moment almost as large as in the vortex lattice phase. At high temperatures, the vortex density rises substantially *above* the solid phase.

This overall increase in M_z is consistent with experiments, but the rise is associated not with the melting itself but rather with the disappearance of phase coherence in the z direction ($\gamma_{zz} \rightarrow 0$), which is also accompanied by dramatic changes in the transport coefficients, R_c and R_{ab} . In 3D, this increase is associated with the proliferation of




FIG. 4. Entropy S (upper panel) and normalized vortex density (lower panel) for $f = 1/24$ and $1/6$ in $24 \times 24 \times 12$ system with open-boundary conditions. The error bars denote the rms deviations from layer to layer.

vortex loops caused by the 3D XY fluctuations. The loops screen the repulsion between vortex lines, allowing them to come closer together and the net vortex density to increase. In 3D, the screening also encourages collision and fusion of field-induced vortex lines [20], causing them to lose the longitudinal phase coherence at T_ℓ .

The rise in M_z for $f = 1/24$ in our model would actually occur over a very narrow temperature range in the real superconductor. This is because J in $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ is strongly temperature dependent near T_c with $J \propto \frac{d\phi_0^2}{16\pi^3\lambda(T)^2}$. Using the simple mean-field form for the temperature dependence of $\lambda(T)$ and material parameters for $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$, we estimate $\Delta T \equiv [T_\ell - T_m] < 150$ mK for $f = 1/24$, and $\Delta T < 10$ mK for $f = 1/6$. Thus the rise in M_z , in fact, could occur over a very narrow temperature range in high- T_c materials, in good agreement with experiments [8,9].

Finally, we consider whether the upper transition in 3D might be a true, second phase transition, and not just a crossover. Numerically, there are several results suggesting a separate phase transition at T_ℓ . First, $\gamma_{zz} \rightarrow 0$ at $T_\ell > T_m$ [14,17,21], and dissipation is due to extensive flux line cutting sets which are both parallel and perpendicular to the field at $T_\ell > T_m$ [17]. An analysis of vortex configurations also reveals that *infinite* clusters of colliding vortex lines and loops first appear at T_ℓ [17], reminiscent of a percolation transition. Recent numerical simulations using the London vortex loop model suggest a similar phase transition, separate from the melting transition [22,23].

Tešanović has considered the low-field regime of the mixed state [7]. By a singular gauge transformation introducing fictitious antivortices, the original problem is transformed into one in which the new-order parameter experiences no applied field but a fluctuating gauge field. The XY -type transition of this new-order parameter (the so-called “ Φ transition”) is a possible candidate for the transition at T_ℓ for $f \leq 1/24$. We emphasize that an increase in M_z at T_ℓ results from the onset of screening by the background vortex loop plasma. It appears that a similar transition between a superfluid and metallic state exists in 2D quantum bosons interacting with strong transverse gauge fluctuations [23,24].

In conclusion, we have calculated the change in magnetization and other properties of the flux lattice in a model high- T_c superconductor near and above the melting transition at *relatively low fields* [25]. The transition proceeds in two stages, a lower melting transition being followed by a broader transition or crossover associated with the proliferation of vortex loops in 3D, or vortex-antivortex pairs in 2D [26]. The magnetization increases sharply at this second stage, in good agreement with recent experimental data.

This work was supported by DOE Grant No. DE-FG02-90 ER45427 through the MISCON, and by NSF Grant No. DMR94-02131.

- [1] M. P. A. Fisher, Phys. Rev. Lett. **62**, 1415 (1989).
- [2] D. R. Nelson and V. M. Vinokur, Phys. Rev. Lett. **68**, 2398 (1992).
- [3] Seungoh Ryu, A. Kapitulnik, and S. Doniach, Phys. Rev. Lett. **77**, 2300 (1996); M. J. P. Gingras and D. A. Huse, Phys. Rev. B **53**, 15 193 (1996); T. Giamarchi and P. L. Doussal, Phys. Rev. B **52**, 1242 (1995).
- [4] R. E. Hetzel, A. Sudbø, and D. A. Huse, Phys. Rev. Lett. **69**, 518 (1992).
- [5] R. Šašik and D. Stroud, Phys. Rev. Lett. **75**, 2582 (1995).
- [6] Seungoh Ryu and D. Stroud, Phys. Rev. B **54**, 1320 (1996).
- [7] Z. Tešanović, Phys. Rev. B **51**, 16 204 (1995).
- [8] E. Zeldov *et al.*, Nature (London) **375**, 373 (1995).
- [9] U. Welp *et al.*, Phys. Rev. Lett. **76**, 4809 (1996).
- [10] J. M. Kosterlitz and D. J. Thouless, J. Phys. C **6**, 1181 (1973); R. P. Feynman, in *Progress in Low Temperature Physics*, edited by C. J. Gorter (North-Holland, Amsterdam, 1955), Vol. 1.
- [11] S. Doniach and B. A. Huberman, Phys. Rev. Lett. **42**, 1169 (1979).
- [12] C. Ebner and D. Stroud, Phys. Rev. B **28**, 5053 (1983).
- [13] M. Franz and S. Teitel, Phys. Rev. Lett. **73**, 480 (1994); S. A. Hattel and J. M. Wheatley, Phys. Rev. B **51**, 11 951 (1995).
- [14] Y.-H. Li and S. Teitel, Phys. Rev. B **47**, 359 (1993).
- [15] K. K. Mon and S. Teitel, Phys. Rev. Lett. **62**, 673 (1989).
- [16] E. A. Jagla and C. A. Balseiro, Phys. Rev. Lett. **77**, 1588 (1996).
- [17] Seungoh Ryu and D. Stroud (to be published).
- [18] The free-boundary conditions constitute a perturbation tending to lower the melting temperatures (by about 10% for $f = 1/24$, less than 2% for $f = 1/6$) below their periodic values.
- [19] C. Ebner and D. Stroud, Physica (Amsterdam) **162C-164C**, 1469 (1989).
- [20] We observe that T_ℓ is signaled by the appearance of an “infinite vortex tangle” and by large fluctuations in transverse vorticity, not just by line entanglement and the occurrence of finite vortex loops, both setting in near T_m for thermodynamic samples.
- [21] A. E. Koshelev (unpublished).
- [22] A. K. Nguyen, A. Sudbø, and R. E. Hetzel, Phys. Rev. Lett. **77**, 1592 (1996).
- [23] Tao Chen and S. Teitel, cond-mat/9610151, 1997 (to be published).
- [24] D. K. K. Lee, D. H. Kim, and P. A. Lee, Phys. Rev. Lett. **76**, 4801 (1996).
- [25] For highly anisotropic systems with $J_{xy}/J_z \sim (100-1000)$, we estimate that $f = 1/24$ roughly corresponds to $B \sim (250 - 25)$ G [4,21]. Furthermore, the density of unit vortex segments $|n_z|$ belonging to the field-induced vortices for $f = 1/24$ for $T < T_m$ is less than 50% of those due to vortex loops induced at T_{XY} .
- [26] Representative movies from the simulation may be found at <http://www.physics.ohio-state.edu:80/~ryu/jj.html>.